

## Laser Crystals

### NLO Crystals

### Birefringent Crystals

### AO and EO Crystals

## Neodymium Doped Yttrium Orthovanadate (Nd:YVO4)

### Introductions



Nd:YVO4 is the most efficient laser host crystal for diode pumping among the current commercial laser crystals, especially, for low to middle power density. This is mainly for its absorption and emission features surpassing Nd:YAG. Pumped by laser diodes, Nd:YVO4 crystal has been incorporated with high NLO coefficient crystals (LBO, BBO, or KTP) to

frequency-shift the output from the near infrared to green, blue, or even UV. This incorporation to construct all solid state lasers is an ideal laser tool that can cover the most widespread applications of lasers, including machining, material processing, spectroscopy, wafer inspection, light displays, medical diagnostics, laser printing, and data storage, etc. It has been shown that Nd:YVO4 based diode pumped solid state lasers are rapidly occupying the markets traditionally dominated by water-cooled ion lasers and lamp-pumped lasers, especially when compact design and single-longitudinal-mode outputs are required.

### Basic Properties

Items	Specification
Crystal Structure:	Zircon Tetragonal, space group D <sub>4h</sub> -I <sub>4</sub> /amd
Cell Parameter:	a=b=7.1193 Å, c=6.2892 Å
Density:	4.22g/cm <sup>3</sup>
Atomic Density:	1.26x10 <sup>20</sup> atoms/cm <sup>3</sup> (Nd 1.0%)
Mohs Hardness:	4-5 (Glass-like)
Thermal Expansion Coefficient (300K):	$\alpha_a=4.43 \times 10^{-6}/K$ $\alpha_c=11.37 \times 10^{-6}/K$
Thermal Conductivity Coefficient (300K):	//C: 0.0523W/cm/K ⊥C: 0.0510W/cm/K
Lasing wavelength:	1064nm, 1342nm
Thermal optical coefficient (300K):	dno/dT=8.5×10 <sup>-6</sup> /K dne/dT=2.9×10 <sup>-6</sup> /K
Stimulated emission cross-section:	25×10 <sup>-19</sup> cm <sup>2</sup> @1064nm
Fluorescent lifetime:	90μs(1% Nd doping)
Absorption coefficient:	31.4cm <sup>-1</sup> @810nm
Intrinsic loss:	0.02cm <sup>-1</sup> @1064nm
Gain bandwidth:	0.96nm @1064nm
Polarized laser emission:	π polarization; parallel to optic axis(c-axis)
Diode pumped optical to optical efficiency:	>60%
Sellmeier equations	$n_o^2=3.77834+0.069736/(\lambda^2-0.04724)-0.010813\lambda^2$ $n_e^2=4.59905+0.110534/(\lambda^2-0.04813)-0.012676\lambda^2$

Nd:YVO4

Crystal

YVO4 01

## Laser Crystals

## NLO Crystals

## Birefringent Crystals

## AO and EO Crystals

## Neodymium Doped Yttrium Orthovanadate (Nd:YVO4)

## Laser Properties of Nd:YVO4

1. One most attractive character of Nd:YVO4 is, compared with Nd:YAG, its 5 times larger absorption coefficient in a broader absorption bandwidth around the 808 nm peak pump wavelength, which just matches the standard of high power laser diodes currently available. This means a smaller crystal that could be used for the laser, leading to a more compact laser system. For a given output power, this also means a lower power level at which the laser diode operates, thus extending the lifetime of the expensive laser diode. The broader absorption bandwidth of Nd:YVO4 which may reaches 2.4 to 6.3 times that of Nd:YAG. Besides more efficient pumping, it also means a broader range of selection of diode specifications. This will be helpful to laser system makers for wider tolerance for lower cost choice.

2. Nd:YVO4 crystal has larger stimulated emission cross-sections, both at 1064nm and 1342nm. When a-axis cut Nd:YVO4 crystal lasing at 1064nm, it is about 4 times higher than that of Nd:YAG, while at 1340nm the stimulated cross-section is 18 times larger, which leads to a CW operation completely outperforming Nd:YAG at 1320nm. These make Nd:YVO4 laser be easy to maintain a strong single line emission at the two wavelengths.

3. Another important character of Nd:YVO4 lasers is, because it is an uniaxial rather than a high symmetry of cubic as Nd:YAG, it only emits a linearly polarized laser, thus avoiding undesired birefringent effects on the frequency conversion. Although the lifetime of Nd:YVO4 is about 2.7 times shorter than that of Nd:YAG, its slope efficiency can be still quite high for a proper design of laser cavity, because of its high pump quantum efficiency.

The major laser properties of Nd:YVO4 vs Nd:YAG are listed in Table below, including stimulated emission cross-sections ( $\sigma$ ), Absorption Coefficient ( $\alpha$ ), Fluorescent lifetime ( $\tau$ ), Absorption Length ( $L_a$ ), threshold Power ( $P_{th}$ ) and Pump Quantum Efficiency ( $\eta_s$ ).

Laser Properties of Nd:YVO4 vs Nd:YAG

LASER CRYSTAL	DOPING (atm%)	$\sigma$ ( $\times 10^{-19}$ CM <sup>2</sup> )	$\alpha$ (CM <sup>-1</sup> )	$\tau$ ( $\mu$ s)	$L_a$ (mm)	$P_{TH}$ (mw)	$\eta_s$ (%)
Nd:YVO4(a-cut)	1.0	25	31.2	90	0.32	30	52
	2.0	25	72.4	50	0.14	78	48.6
Nd:YVO4(c-cut)	1.1	7	9.2	90		231	45.5
Nd:YAG	0.85	6	7.1	230	1.41	115	38.6

## Typical Results

Diode pumped Nd:YVO4 laser output comparing with diode pumped Nd:YAG laser.

Crystals	Size (mm <sup>3</sup> )	Pump Power	Output (at 1064nm)
Nd:YVO4	3x3x1	850mW	350mW
Nd:YVO4	3x3x5	15W	6W
Nd:YAG	3x3x2	850mW	34mW

Nd:YVO4

Crystal

YVO4 01

Diode pumped Nd:YVO4+KTP green laser.

8W green laser was generated from a 15W LD pumped 0.5%Nd:YVO4 with

## Laser Crystals

## NLO Crystals

## Birefringent Crystals

## AO and EO Crystals

## Neodymium Doped Yttrium Orthovanadate (Nd:YVO4)

## Laser Properties of Nd:YVO4

intracavity KTP.

200mW green outputs are generated from 1 W LD pumped 2%Nd:YVO4 lasers by using Banner Union's 2x2x5mm KTP and 3x3x1mm Nd:YVO4.

2-5mw green outputs are generated from 180mw LD pumped 3%Nd:YVO4 and KTP glued crystals. For more details, please refer to Glued Crystals.

## Coating Service

- ◇ Both ends AR/AR-1064/808nm,  $R < 0.2\% @ 1064\text{nm}$ ,  $R < 2\% @ 808\text{nm}$
- ◇ S1:HR@1064&532 nm, HT808 nm,  
 $R > 99.8\% @ 1064\&532\text{nm}$ ,  $T > 90\% @ 808\text{nm}$   
S2:AR@1064&532 nm,  $R < 0.2\% @ 1064\text{nm}$ ,  $R < 0.5\% @ 532\text{nm}$
- ◇ S1:HR@1064, HT808,  $R > 99.8\% @ 1064\text{nm}$ ,  $T > 95\% @ 808\text{nm}$   
S2:AR@1064,  $R < 0.1\% @ 1064\text{nm}$ .
- ◇ S1,S2 AR-coated, S3:gold/chrome plated.
- ◇ Both ends AR/AR-1064 nm; S3:AR-808 nm
- ◇ Other coatings are available upon request.

## Stand Specifications

Items	Specifications
Dimension Tolerance	$(W \pm 0.1\text{mm}) \times (H \pm 0.1\text{mm}) \times (L + 0.5/-0.1\text{mm})$ ( $L \geq 2.5\text{mm}$ )
	$(W \pm 0.1\text{mm}) \times (H \pm 0.1\text{mm}) \times (L + 0.2/-0.1\text{mm})$ ( $L < 2.5\text{mm}$ )
Clear aperture	central 90% of the diameter
Flatness	$\leq \lambda/8 @ 632.8\text{nm}$ ( $L \geq 2.5\text{mm}$ )
	$\leq \lambda/4 @ 632.8\text{nm}$ ( $L < 2.5\text{mm}$ )
wavefront distortion	$\leq \lambda/4 @ 632.8\text{nm}$
Bevel	$\leq 0.2\text{mm} @ 45^\circ$
Chip	$\leq 0.1\text{mm}$
Surface Quality	scratch and dig 10-5
Parallelism	$\leq 20$ arc seconds
Perpendicularity	$\leq 5$ arc minutes
Angle tolerance	$\leq 0.5^\circ$
Damage threshold[GW/cm ]:	$> 1$ for 1064nm, TEM00, 10ns, 10Hz (AR-coated)

Nd:YVO4

Crystal

YVO4 01